



Magic HS

2K acrylic clear coat



EASY APPLICATION HIGH BRILLIANCE

**SCRUB
RESISTANT**

FEATURES

- suitable for all types of base coat
- flow property similar to the original paint
- non-yellowing



Ease of application



Brilliance



Car wash brush resistance



Ease of polishing



Code 1335



HARDENER'S UTILIZATION

Small repair (1 panel)



Use hardener
Fast code 4500

Medium repair (3-5 panels)



Use hardener
Standard code 4300

Total repair



Use hardener
Slow code 4100

PRODUCT PREPARATION



1 Shake slightly the product, take the required quantity and add the hardener.



Shake




Mixing ratio
2:1 by volume

2 If necessary, to thin 0-10%.

Diluyente per Acrilici code 1653
Diluyente per Acrilici Lento code 1648

APPLICATION



1 After complete drying of the base coat, apply 1 coat of **MAGIC HS** code 1335.



Air mix spray gun or high transfer
nozzle 1,2-1,4 pressure 2-3 bar

2 Apply a second coat of **MAGIC HS** code 1335.



Thickness 50 micron
dry film with two coats

DRYING TIME

	DUST FREE	BY TOUCH	POLISH
AIR DRYING 20°C 65% R.H.	10-15 minutes	3-4 hours	24 hours
OVEN 60°C	-	-	30 minutes
I.R. LAMPS	(Follow manufacturer's instructions)		